

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Dott.Gallina s.r.l
Strada Carignano 104
10040 La Loggia Italy
Italy

Test Number : 16-006711
Issue Date : 30/05/2017
Print Date : 30/05/2017
Order Number : 92689

Replacement of Initial Report dated :24/05/2017

Sample Description Clients Ref : "ArcoPlus 547 UV-Tech"
Multiwall modular panel, 7 Wall
Colour : Satin Clear
Nominal Composition : >.98% Polycarbonate with UV_protection UV Tech
Nominal Thickness : 40mm

SAE J2527-2004

Performance Based Standard for the Accelerated Exposure of Automotive Exterior Materials Using a Controlled Irradiance Water Cooled Xenon Arc Apparatus

Colour Change 3-4
Change in Appearance Yellower
Exposure Amount 2500 kJ/m²

Grey Scales in accordance with ISO 105-A02-1993 used for assessing change in colour, where 1 = Significant Change and 5 = No Change

93032

16827

Page 1 of 1

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR